

Technical Data Sheet

Thermoplastic Polyurethane

■ Feature

Excellent physical property, Good hydrolysis and microbial Resistance, easy&stable process etc.

■ **Application:** Automotive cable, electronic cable.

■ **Processing:** Injection, Extrusion etc.

■ Properties

Item	Test Method	Value
Yellow Index(Yi)	ASTM-E313	1.7
Specific gravity (g/cm ³)	ASTM-D792	1.12
Hardness (Shore A)	ASTM-2240	81±1
Tensile strength(MPa)	ASTM-D412	32
100% Modulus(MPa)	ASTM-D412	6.5
300% Modulus(MPa)	ASTM-D412	10.5
Elongation at break (%)	ASTM-D412	680
Tear strength (KN/m)	ASTM-D624	103
Abrasion(mm ³)	ASTM-D5963	30
Flow Beginning Point (°C)	/	172

■ Processing Guide

For optimum results, previous drying of the product during 2-3 hours at 100~110°C is advisable, in a hot air circulatory, vacuum desiccate-air dryer.

■ Package & Storage

25kg/bag

Never put opened packages exposed in open air for prolonged periods of time during molding and processing.

Because of the high moisture absorbing property, TPU products should be well stored in a dry, cool and shady area.

■ Note

These are typical values and should not be used as specifications.

SHANDONG INOV POLYURETHANE CO., LTD.

Add: Polymer and Auxiliary Material Zone, High-Tech District, Zibo City, Shandong Province,

China Tel: +86-533-3598719

Web: <http://www.inov-chem.com>